


1) Generalités

a) La monture

- Polypropylène
- Agrafage inoxydable

b) Monolame

- SEBS



2) Dimensions, coloris, références et poids

Dimensions	w	g	b	r	y	Poids (kg)
30cm	100356	100363	100370	100387	100394	0.165
40cm	100455	100462	100479	100486	1007493	0.215
60cm	100653	100660	100677	100684	100691	0.315
Joint pivotant	100950	100967	100974	100981	100998	0.050

3) Spécifications techniques

Stérilisable à 134 °

Avant utilisation : Nous vous conseillons de nettoyer/stériliser l'article avant usage.

4) Informations supplémentaires

a) Secteur alimentaire

Notre collection de raclettes monolame est conforme aux normes HACCP. Notre ligne de code couleur (blanc-rouge-bleu-jaune-vert) aidera les gestionnaires de la qualité à éviter la contamination croisée pendant la production.

b) Accessoires

Nos manches HACCP en fibre de verre et Hygi Pro peuvent être utilisés avec notre collection de raclettes monolame.



Fiche Technique
INDUSTRA FOOD
MONOLAME
Filet français
Full colour

Chemical resistance of general Cawiton® SBS and SEBS grades

Acetic acid, 5 %	S
Acetone	U
Ammonia	S
Bleach	L
Butter	L
Cola beverage	S
Detergent, 30 %	S
Ethyl acetate	U
Ethylalcohol, diluted	S
Ethylalcohol, 96 %	L
Gasoline	U
Hydrochloric acid, 3 N	S
Hydrogen peroxide, 6 %	S
Mayonaise	L
Ketchup	S
Hand lotion	S
Methylalcohol	L
Milk	E
Mineral oil	L
Nitric acid, 3 N	S
Orange juice	S
Salad oil	L
Sodium hydroxide, 3 N	S
Sulfuric acid	S
Terpentine	U
Toluene	U
Water	E

E = Excellent
S = Satisfactory
L = Limited
U = Unsatisfactory



Chemical resistance of Cawiton compounds

1 Acetaldehyde	R	73 Ethyl bromide	R	145 Oils vegetable	T
2 Acetates (low mol wt)	R	74 Ethyl chloride	R	146 Oleic acid	R
3 Acetic acid (less then 5%)	R	75 Ethylamine	R	147 Oxalic acid	R
4 Acetic acid (more then 5%)	R	76 Ethylene chlorohydrin	R	148 Oxygen (gas)	R
5 Acetic anhydride	T	77 Ethylene dichloride	R	149 Ozone	R
6 Aceto nitrile	T	78 Ethylene glycol	T	150 Perchloric acid	R
7 Acetone	T	79 Ethylene oxide	R	151 Perchloroethylene	T
8 Acetyl bromide	R	80 Fatty acids	T	152 Phenol	N
9 Acetyl chloride	R	81 Ferric chloride	R	153 Phosphoric acid (ortho)	R
10 Air	R	82 Ferric sulfate	R	154 Phthalic acid	N
11 Alcohols	T	83 Ferrous chloride	R	155 Plating solutions	R
12 Aliphatic hydrocarbons (C4 and higher)	N	84 Ferrous sulfate	R	156 Polyglycol	T
13 Aluminium chloride	R	85 Fluoborate salts	R	157 Potassium carbonate	R
14 Aluminium sulphate	R	86 Fluoboric acid	R	158 Potassium chlorate	R
15 Alums	R	87 Fluo-silicic acid	R	159 Potassium hydroxide (med.conc.)	R
16 Ammonia (gas, liquid)	R	88 Formaldehyde	R	160 Potassium hydroxide (conc.)	R
17 Ammonium acetate	R	89 Formic acid	R	161 Potassium iodide	R
18 Ammonium carbonate	R	90 Freon	T	162 Propinal Adehyde	R
19 Ammonium chloride	R	91 Gasoline (non-aromatic)	N	163 Pyridine	R
20 Ammonium hydroxide	R	92 Gasoline (high-aromaticity)	N	164 Sea water	R
21 Ammonium nitrate	R	93 Glucose (dextrose)	R	165 Silicone fluids	R
22 Ammonium phosphate	R	94 Glue (water base)	R	166 Silicone oil	R
23 Ammonium sulfate	R	95 Glycerine	T	167 Silver nitrate	R
24 Amyl acetate	N	96 Grease	T	168 Skydrol	N
25 Amyl alcohol	N	97 Hydriodic acid	R	169 Soap solutions	R
26 Amyl chloride	N	98 Hydro bromic acid	R	170 Sodium bicarbonate	R
27 Aniline	T	99 Hydrochloric acid	R	171 Sodium bisulfate	R
28 Aniline hydrochloride	T	100 Hydrochloric acid (med.conc.)	R	172 Sodium bisulfite	R
29 Antimony salts	R	101 Hydrochloric acid (conc.)	R	173 Sodium borate	R
30 Aqua regia (75% HC1 25% HNO ³)	R	102 Hydrocyanic acid	R	174 Sodium carbonate	R
31 Aromatic hydrocarbons	N	103 Hydrofluoric acid	R	175 Sodium chlorate	R
32 Arsenic salts	R	104 Hydrogen peroxide (dil.)	R	176 Sodium chloride	R
33 Barium salts	R	105 Hydrogen peroxide (conc.)	R	177 Sodium terrocyanide	R
34 Benzaldehyde	N	106 Hydrogen sulfide	T	178 Sodium hydrosulfite	R
35 Benzene	N	107 Hypochlorous acid	R	179 Sodium hydroxide (dil.)	R
36 Benzene sulfonic acid	R	108 Iodine and solutions	T	180 Sodium hydroxide (med.conc.)	R
37 Benzoic acid	N	109 Iron salts	R	181 Sodium hydroxide (conc.)	R
38 Benzyl alcohol	N	110 Isopropanol (IPA)	R	182 Sodium hypochlorite (below 5%)	R
39 Bleaching liquors (non aromatic)	R	111 Kerosene	N	183 Sodium hypochlorite (above 5%)	R
40 Boric acid	R	112 Ketones (water soluble)	R	184 Sodium nitrate	R
41 Bromine	R	113 Lactic acids	R	185 Sodium silicate	R
42 Break fluid	R	114 Laquer solvents	N	186 Sodium sulfide	R
43 Butane	N	115 Lactic acids	R	187 Sodium sulfite	R
44 Butyl acetate	N	116 Lead Acetate	R	188 Steam (up to 40 psi)	T
45 Buryl alcohol (Butanol)	T	117 Linseed Oil	N	189 Stearic acid	R
46 Butyric acid	R	118 Lithium hydroxide	R	190 Styrene	N
47 Calcium oxide (diluted)	R	119 Magnesium chloride	R	191 Sulfur chloride	R
48 Calcium salts	R	120 Magnesium sulfate	R	192 Sulfur dioxide	R
49 Carbon (di)sulfide	N	121 Malic acid	R	193 Sulfuric hezafluoride	R
50 Carbon dioxide	R	122 Manganese salts	R	194 Sulfuric trioxide	R
51 Carbon tetrachloride	T	123 Mercury salts	R	195 Sulfuric acid (dil.)	R
52 Chloroacetic acid	R	124 Methane	N	196 Sulfuric acid (med.conc.)	R
53 Chlorine (wet)	R	125 Methanol (<40%)	R	197 Sulfuric acid (conc.)	R
54 Chlorine (dry)	R	126 Methanol (>40%)	T	198 Sulfurous acid	R
55 Chlorobenzene	N	127 Methyl chloride	R	199 Swimming pool water	R
56 Chlorobromomethane	N	128 Methyl-ethyl-ketone (MEK)	R	200 Tannic acid	R
57 Chloroform	N	129 Methylen chloride	R	201 Tanning extracts	R
58 Chlorosulfonic acid	R	130 Milk	R	202 Tataric acid	R
59 Chromic acid	R	131 Mixes acid (40% sulphuric 15% nitric)	R	203 Tin salts	R
60 Chromium salts	R	132 Molybdenum disulfide	R	204 Titanium salts	R
61 Citric Acid	R	133 Monoethanolamine	T	205 Toluene (toluol)	N
62 coolant	R	134 Naphtha	N	206 Trichloroacetic acid	R
63 Copper salts	R	135 Natural gas	N	207 Trichloroethylene	N
64 Cresol	N	136 Nickel salts	R	208 Tri-sodium	R
65 Cyclohexane	N	137 Nitric acid (diluted)	R	209 Turpentine	N
66 Cyclohexanone	N	138 Nitric acid (med. Conc.)	R	210 Urea	R
67 Diacetone alcohol	R	139 Nitric acid (conc.)	R	211 Uric Acid	N
68 Dimethyl formamide	R	140 Nitrobenzene	N	212 Vinyl plastisol	N
69 Essential oils	R	141 Nitrogen oxides	R	213 Water	R
70 Ethers	N	142 Nitrous acid	R	214 Water (brine)	R
71 Ethyl acetate	R	143 Oils animal	T	215 Xylene (Xylol)	N
72 Ethyl alcohol (Ethanol)	T	144 Oils mineral	T	216 Zinc chloride	R

R: resistant

N: not resistant

T: testing recommended before use

